



(11) **EP 1 445 812 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
11.08.2004 Bulletin 2004/33

(51) Int Cl.⁷: **H01M 6/08, H01M 4/52,**
H01M 4/62, H01M 4/66,
H01M 10/30

(21) Application number: **02801572.5**

(22) Date of filing: **15.10.2002**

(86) International application number:
PCT/JP2002/010683

(87) International publication number:
WO 2003/034520 (24.04.2003 Gazette 2003/17)

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR

(30) Priority: **17.10.2001 JP 2001319855**
17.10.2001 JP 2001319857
17.10.2001 JP 2001319858

(71) Applicant: **Sony Corporation**
Tokyo 141-0001 (JP)

(72) Inventors:
• **TAKAHASHI, Akio,**
c/o SONY FUKUSHIMA CORPORATION
Koriyama-shi, Fukushima 963-0531 (JP)
• **MORIKAWA, Shinichiro,**
c/o SONY CORPORATION
Tokyo 141-0001 (JP)

• **HAYASHI, Naoki, c/o SONY CORPORATION**
Tokyo 141-0001 (JP)
• **HONDA, Kazuo,**
c/o SONY FUKUSHIMA CORPORATION
Koriyama-shi, Fukushima 963-0531 (JP)
• **OYA, Kuniyasu,**
c/o SONY FUKUSHIMA CORPORATION
Koriyama-shi, Fukushima 963-0531 (JP)
• **YAMAMOTO, Kenta, c/o SONY CORPORATION**
Tokyo 141-0001 (JP)
• **KOBAYASHI, Noriyuki,**
SONY FUKUSHIMA CORPORATION
Koriyama-shi, Fukushima 963-0531 (JP)

(74) Representative: **Müller - Hoffmann & Partner**
Patentanwälte,
Innere Wiener Strasse 17
81667 München (DE)

(54) **ALKALINE BATTERY**

(57) The present invention provides an alkaline battery suitable for use as a primary or secondary battery as a power source of electronic appliances. The battery is excellent in discharge characteristics under a heavy load and in cycle characteristics.

The alkaline battery (100) comprises a cathode mix (3) containing β -nickel oxy-hydroxide, an anode mix (5) containing zinc as a main component of anode active material, and an alkali solution as an electrolyte, wherein the cathode mix (3) includes a mixture of β -nickel oxy-hydroxide, graphite powder, and a potassium hydroxide solution in a given weight ratio. The β -nickel oxy-hydroxide is prepared by chemical oxidation and has an approximately spherical shape of particle with a mean particle size in the range of 5 to 50 μm .

FIG. 3

